

GEDA KRONOS

Waterproofing membrane

DESCRIPTION

Pre-fabricated waterproofing membrane made of distilled bitumen and elastomeric polymers SBS and CPB (blend of copolymer polyolefin's) from metallocene catalysis polymerization, reinforced with a woven non woven single strand composite polyester, which gives the membrane high mechanical characteristics and excellent dimensional stability.

The P version, on the upper face, has a woven non woven polypropylene finish which improves the walk ability and allows for immediate coating.

The particular upper face finish has multiple advantages, of which:

- improved aesthetics;
- improved walkability on the membrane;
- improved coefficient of friction, preventing slippages especially on sloped roofs;
- easier to coat and time savings (can be done immediately after application) as well as aesthetics;
- increased tear resistance. Very useful when mechanically fixing, as it increases the overall performance of the fixing of the washer (less deformation);
- ease of application also of the overlaps whereas the polypropylene mat is perfectly compatible with the waterproofing mass and actually increases the adhesion between the layers.

The PA versions are self protected on the upper face with mineral slates which reduce superficial heat absorption improving the durability of the membrane.

METHODS OF APPLICATION

For the application of the membrane the use of heat is generally used by means of a gas torch or specific hot air machine. Use protective devices required by law. The application by heat is not suggested when on heat sensitive materials (polystyrene insulation).

- Coordinate the operations in a way to not cause damage to the construction elements and underground structure. Avoid to leave the structure for the night or for periods of prolonged work interruptions without having been properly sealed.
- **The application surface must not have any depressions to avoid the risk of ponding water, the slope must be at least 1.5% on concrete decks and 3% for steel or wooden ones, this to guarantee a proper run off of rainwater.**
- The water drainage spouts should be sufficiently big enough to allow for rain water to be eliminated in an efficient way.
- Prepare cementitious substrates, including verticals and details, with a bituminous primer either by brush or airless, approx. 300/400 g/m².
- Allow this preparation layer to dry before proceeding with any other operation.
- With prefabricated constructions, apply a suitable reinforcing strip along all joints. In the presence of construction joints, prefabricated panels or metal decks, suitable expansion joints are to be considered.
- The membranes must be applied to the substrate fully bonded.
- All details, perimeters, verticals, change of slope as well as projecting area must be fully bonded.

For further information and news it is recommended to consult the GEDACO technical literature; our Technical Office is always available to evaluate particular problems and to provide the necessary assistance to best apply our waterproofing membranes.

FIELDS OF USE

EN13707 CONTINUOUS ROOFS 0958-CPR-2045/1
DOUBLE LAYER / MULTILAYER
TORCH / MECHANICAL FIXING APPLICATION (only P)
FULLY BONDED APPLICATION
COMPLIMENTARY LAYER (only P) / TOP LAYER (only PA) / HEAVY PROTECTION (P 4 mm)
EN13859-1 UNDER ROOF TILE (ONLY PA)
SINGLE LAYER / DOUBLE LAYER / MULTILAYER
TORCH / MECHANICAL FIXING APPLICATION
FULLY BONDED APPLICATION
TOP LAYER
EN13969 RETAINING WALLS 0958-CPR-2045/1
SINGLE LAYER / DOUBLE LAYER / MULTILAYER
TORCH APPLICATION
FULLY BONDED APPLICATION
COMPLIMENTARY LAYER / TOP LAYER

APPLICATION

- On cementitious surfaces and similar apply, by roller or airless, bituminous primer, approx. consumption 300 g/m².
- Apply by torch application a 25 cm strip of membrane reinforced with polyester along all vertical up stands.
- To have all overlaps with the slope, position the membrane always starting from the lowest point.
- Position the membrane sheets staggered, avoiding to create any overlaps against the slope and the drains.
- Cut the corners of membrane sheet which will be laid under the next sheet at a 45° angle (10 x 10 cm).
- The joints, both side and head, must be respectively overlapped by 10 & 15 cm.
- The second layer of membrane will be applied astride and over the first one, always in the same direction, and approx. 1/4 of its length from the previous sheet.
- The bituminous membrane will be applied with a propane gas torch to the substrate. It is necessary to heat the entire surface, except for the side & head laps, making sure that the compound forms a liquid mass in front of the roll to assure that it saturates any superficial porosity.
- The side laps (10 cm) and head laps (15 cm) will be heat welded with an appropriate torch; during this stage the overlaps should be pressed by using a roller (15 kg) from which a bead of compound should flow and therefore avoiding to have to iron the overlaps.
- Apply the vertical membrane sheet having the same characteristics of the waterproofing membrane and dimensions equal to the width of the roll, making sure that it overlaps the horizontal one by at least 10 cm, heating it with a gas torch and squeezing it with a trowel until a bead of compound appears from underneath.
- The height of the verticals must be equivalent or superior to the finished surface by at least 15 cm.



TECHNICAL DATA

TECHNICAL CHARACTERISTICS	MEASURE UNITS	REFERENCE NORM	P		PA		TOLERANCE	
Type of reinforcement			Single strand polyester					
Upper face finish			Polypropylene mat		Mineral *			
Lower face finish			Polypropylene film					
Length	m	EN 1848-1	10 -1%					
Width	m	EN 1848-1	1 -1%					
Thickness	mm	EN 1849-1	3	4			±5%	
Mass	kg/mq	EN 1849-1			4,0	4,5	±10%	
Cold flexibility	°C	EN 1109	-20					
Flow resistance	°C	EN 1110	110					
Shear resistance L/T	N/5 cm	EN 12317-1	400 / 300					-20%
Tensile strength L/T	N/5 cm	EN 12311-1	500 / 400					-20%
Elongation at break L/T	%	EN 12311-1	35 / 35					-15
Tearing resistance L/T	N	EN 12310-1	140 / 140					-30%
Static puncture resistance	kg	EN 12730	10					
Dynamic puncture resistance	mm	EN 12691	800					
Dimensional stability	%	EN 1107-1	-0,3					
Loss mineral	%	EN 12039				30		
Fire resistance		EN 13501-5	F ROOF					
Fire reaction		EN 13501-1	F					
Watertightness	kPa	EN 1928	60					
Impermeability after artificial ageing	kPa	EN 1926	60					

Note: NPD = No Performance Declared in accordance with the EU Construction Products Directive.

* Mineral self-protected products may undergo color tone variations due to the time and length of storage. Exposure to atmospheric conditions, after application, will tend to uniform the color after a few months. The change in color tone cannot therefore be contested and / or complained of as it is a natural phenomenon that the slate manufacturer himself cannot guarantee.

RECOMMENDATIONS

To best use the technical characteristics of bituminous membranes and guarantee the maximum performance and durability of the jobs where they are used, some simple but fundamental rules must be respected.

- The rolls are to be stored in an upright position, indoors in a dry and ventilated area, away from heat sources. Absolutely avoid the stacking of rolls and pallets for storage or transport to avoid possible deformations which may compromise a perfect installation. It is recommended to store the product at temperatures above 0°C.
- The rolls shall be kept in a warm or heated storage area during application, should the workability of the material deteriorate or become stiff and difficult to install during application, these should be returned to the heated storage area and substituted with new rolls. The rolls that are temporarily stored on the roof before application, shall be kept elevated by being left on their own pallets and shall be covered and protected from the weather.
- The application surface must be smooth dry & clean.
- The application surface must be previously treated with a suitable bituminous primer, to eliminate dust and enhance the adhesion of the membrane.
- The application surface must not have any depressions to avoid the risk of ponding water, the slope must be at least 1.5% on concrete decks and 3% for steel or wooden ones, this to guarantee a proper run off of rainwater.
- In situations of application on vertical surfaces superior to 2 meters or on very sloped substrates, apply suitable mechanical fixings to the head laps, after which they will be sealed when torching the head laps.
- The application must be done at temperature higher than +5°C.
- The application must be interrupted in adverse weather conditions (high humidity, rain, etc.).
- Roofs waterproofed with elastomeric membranes must have the last layer self protected with mineral slates. As an alternative, depending on the type of structure, it is possible to use heavy protection (gravel, floating pavements, etc.).
- The pallets on which the rolls are packaged are intended for normal warehouse use.
- The materials on stock should be rotated following a first in first out rotation.

SIZES AND PACKING

	P 3 mm	P 4 mm	PA 4,0 kg/m ²	PA 4,5 kg/m ²
Rolls size [m]	10 x 1	10 x 1	10 x 1	10 x 1
Rolls per pallet	30	25	30	25
Square meters per pallet [m ²]	300	250	300	250

Sizes & packing may vary depending on the type of transportation.