

GEDA VIADUCT

Waterproofing membrane

DESCRIPTION

Pre-fabricated waterproofing membrane made of distilled bitumen and elasto-plastic polymers (APP), reinforced with a woven non woven single strand composite polyester fabric, with very high mechanical characteristics and resistance to both static and dynamic puncture.

The particular structure of these products make them suitable for the waterproofing of complex works where the stress on the waterproofing system require the use of products with proven reliability.

Due to the characteristics, the membranes of the GEDA VIADUCT series are used with success for the waterproofing of both civil and industrial works, in particular for those with great mechanical stress such as: bridges, viaducts, water works, foundations, parking lots.

METHODS OF APPLICATION

For the application of the membrane the use of heat is generally used by means of a gas torch or specific hot air machine. Use protective devices required by law. The application by heat is not suggested when on heat sensitive materials (polystyrene insulation).

- Coordinate the operations in a way to not cause damage to the construction elements and underground structure. Avoid to leave the structure for the night or for periods of prolonged work interruptions without having been properly sealed.
- **The application surface must not have any depressions to avoid the risk of ponding water, the slope must be at least 1.5% on concrete decks and 3% for steel or wooden ones, this to guarantee a proper run off of rainwater.**
- The water drainage spouts should be sufficiently big enough to allow for rain water to be eliminated in an efficient way.
- Prepare cementitious substrates, including verticals and details, with a bituminous primer either by brush or airless, approx. 300/400 g/m².
- Allow this preparation layer to dry before proceeding with any other operation.
- With prefabricated constructions, apply a suitable reinforcing strip along all joints. In the presence of construction joints, prefabricated panels or metal decks, suitable expansion joints are to be considered.
- The membranes must be applied to the substrate fully bonded.
- All details, perimeters, verticals, change of slope as well as projecting area must be fully bonded.
- If using the membrane for application under hot asphalt, the thickness of the binder course must be minimum 6 cm with a granulometry of 0-15 mm, while for the surface course the thickness must be minimum 4 cm and granulometry of 0-12 mm.
- In case of use on refurbishments, the product must be applied on original support (all existing waterproofing layers must be removed). On the clean application surface it must applied PRIMER EPOX, as indicated in the product technical data sheet.

For further information and news it is recommended to consult the GEDACO technical literature; our Technical Office is always available to evaluate particular problems and to provide the necessary assistance to best apply our waterproofing membranes.

FIELDS OF USE

ENI3707 CONTINUOUS ROOFS 0958-CPR-2045/I
DOUBLE LAYER / MULTILAYER
TORCH APPLICATION
FULLY BONDED APPLICATION
COMPLIMENTARY LAYER / HEAVY PROTECTION
ENI4695 VIADUCTS 0958-CPR-2045/I
SINGLE LAYER / DOUBLE LAYER / MULTILAYER
TORCH APPLICATION
FULLY BONDED APPLICATION
COMPLIMENTARY LAYER / HEAVY PROTECTION

APPLICATION

- On cementitious surfaces and similar apply, by roller or airless, bituminous primer, approx. consumption 300 g/m².
- Apply by torch application a 25 cm strip of membrane reinforced with polyester along all vertical up stands.
- To have all overlaps with the slope, position the membrane always starting from the lowest point.
- Position the membrane sheets staggered, avoiding to create any overlaps against the slope and the drains.
- Cut the corners of membrane sheet which will be laid under the next sheet at a 45° angle (10 x 10 cm).
- The joints, both side and head, must be respectively overlapped by 10 & 15 cm.
- The second layer of membrane will be applied astride and over the first one, always in the same direction, and approx. 1/4 of its length from the previous sheet.
- The bituminous membrane will be applied with a propane gas torch to the substrate. It is necessary to heat the entire surface, except for the side & head laps, making sure that the compound forms a liquid mass in front of the roll to assure that it saturates any superficial porosity.
- The side laps (10 cm) and head laps (15 cm) will be heat welded with an appropriate torch; during this stage the overlaps should be pressed by using a roller (15 kg) from which a bead of compound should flow and therefore avoiding to have to iron the overlaps.
- Apply the vertical membrane sheet having the same characteristics of the waterproofing membrane and dimensions equal to the width of the roll, making sure that it overlaps the horizontal one by at least 10 cm, heating it with a gas torch and squeezing it with a trowel until a bead of compound appears from underneath.
- The height of the verticals must be equivalent or superior to the finished surface by at least 15 cm.



TECHNICAL DATA

| TECHNICAL CHARACTERISTICS | MEASURE UNITS | REFERENCE NORM | P | | TOLERANCE |
|--|-------------------|----------------|-------------------------|-------|-----------|
| Type of reinforcement | | | Single strand polyester | | |
| Upper face finish | | | Sand or talc | | |
| Lower face finish | | | PE film | | |
| Length | m | EN 1848-1 | 10 -1% | 8 -1% | |
| Width | m | EN 1848-1 | 1 -1% | | |
| Thickness | mm | EN 1849-1 | 4 | 5 | ±5% |
| Cold flexibility | °C | EN 1109 | -10 | | |
| Flow resistance | °C | EN 1110 | 120 | | |
| Tensile strength L/T | N/5 cm | EN 12311-1 | 1200 / 1000 | | -20% |
| Elongation at break L/T | % | EN 12311-1 | 45 / 45 | | -15 |
| Tearing resistance L/T | N | EN 12310-1 | 300 / 300 | | -30% |
| Static puncture resistance | kg | EN 12730 | 25 | | |
| Dynamic puncture resistance | mm | EN 12691 | 1750 | | |
| Dimensional stability | % | EN 1107-1 | -0,5 | | |
| Fire resistance | | EN 13501-5 | F ROOF | | |
| Fire reaction | | EN 13501-1 | F | | |
| Watertightness | kPa | EN 1928 | 60 | | |
| Bond strenght | N/mm ² | EN 13596 | 0,49 | | ≥ |
| Shear strenght | N/mm ² | EN 13653 | 0,23 | | ≥ |
| Compatibility by heat conditioning | % | EN 14691 | 177 | | ≥ |
| Crack Bridging Ability | °C | EN 14224 | - 10 | | ≥ |
| Resistance to dynamic water pressure | | EN 14694 | pass | | |
| Resistance to compaction of an asphalt layer | | EN 14692 | pass | | |
| Behaviour of bitumen sheets during application of mastic asphalt | %, mm, % | EN 14693 | NPD | | |

Note: NPD = No Performance Declared in accordance with the EU Construction Products Directive.

RECOMMENDATIONS

To best use the technical characteristics of bituminous membranes and guarantee the maximum performance and durability of the jobs where they are used, some simple but fundamental rules must be respected.

- The rolls are to be stored in an upright position, indoors in a dry and ventilated area, away from heat sources. Absolutely avoid the stacking of rolls and pallets for storage or transport to avoid possible deformations which may compromise a perfect installation. It is recommended to store the product at temperatures above 0°C.
- The rolls shall be kept in a warm or heated storage area during application, should the workability of the material deteriorate or become stiff and difficult to install during application, these should be returned to the heated storage area and substituted with new rolls. The rolls that are temporarily stored on the roof before application, shall be kept elevated by being left on their own pallets and shall be covered and protected from the weather.
- The application surface must be smooth dry & clean.
- The application surface must be previously treated with a suitable bituminous primer, to eliminate dust and enhance the adhesion of the membrane.
- The application surface must not have any depressions to avoid the risk of ponding water, the slope must be at least 1.5% on concrete decks and 3% for steel or wooden ones, this to guarantee a proper run off of rainwater.
- In situations of application on vertical surfaces superior to 2 meters or on very sloped substrates, apply suitable mechanical fixings to the head laps, after which they will be sealed when torching the head laps.
- The application must be done at temperature higher than +5°C.
- The application must be interrupted in adverse weather conditions (high humidity, rain, etc.).
- The pallets on which the rolls are packaged are intended for normal warehouse use.
- The materials on stock should be rotated following a first in first out rotation.

SIZES AND PACKING

| | P 4 mm | P 5 mm |
|--|-----------|-----------|
| Rolls size [m] | 10 x 1 | 8 x 1 |
| Rolls per pallet | 24 | 23 |
| Square meters per pallet [m ²] | 240 | 184 |

Sizes & packing may vary depending on the type of transportation.